



FEEL THE SW DIFFERENCE<sup>®</sup>

# DESIGNED TO ENHANCE WORKER PERFORMANCE.

## PowerForm<sup>®</sup>

### PF-95GW

POWDER-FREE ECOTEK BIODEGRADABLE NITRILE EXAMINATION GLOVES WITH ENERGEL AND BREACH ALERT\*


### EXPERIENCE ENERGEL INFUSED GLOVES, DESIGNED TO HYDRATE SKIN AND PROTECT AGAINST LONG-TERM GLOVE USAGE





- EnerGel<sup>®</sup> Hand Conditioning Technology clinically proven to hydrate and soothe skin
- Breach Alert<sup>®</sup> Visual Detection Technology provides durable 2-ply construction and contrasting inner color
- EcoTek<sup>®</sup> Biodegradable Technology accelerates landfill breakdown without any performance loss\*
- Proven resistance to fentanyl and gastric acid for over 4 hours to replicate hazardous settings and overdose conditions\*
- Silicone-free for critical environments
- Exceeds 1.5 AQL laboratory standards

Optimal thickness for durability and tactile sensitivity

Fully textured surface for wet and dry grip

Tear-resistant beaded cuff for easy donning



PF		PF-95GW			EcoTek
WEIGHT	LENGTH	THICKNESS	FEATURES	COLOR	
 6.5g (large size)	 9.5"	 4.9 mil	EnerGel <sup>®</sup> Breach Alert <sup>®</sup> EcoTek <sup>®</sup>	 GREEN WHITE	



SW<sup>®</sup>  
33278 Central Avenue, Unit 102, Union City, CA 94587, USA  
Tel: +1.510.429.8692 | Fax: +1.510.487.5347

Trademarks and registered trademarks are the property of SW and its affiliates.  
©2022 SW. All rights reserved.



\*Using ASTM D6978

## TECHNICAL DATA



### PF-95GW

POWDER-FREE ECOTEK BIODEGRADABLE  
NITRILE EXAMINATION GLOVES WITH ENERGEL  
AND BREACH ALERT\*

## PRODUCT DESCRIPTION

### SPECIFICATIONS

<b>PRODUCT</b>	PowerForm®		
<b>GRADE</b>	Powder-Free Exam		
<b>MATERIAL</b>	Nitrile		
<b>THICKNESS</b>	<b>FINGER</b>	5.9mil	0.15mm
	<b>PALM</b>	4.9mil	0.13mm
	<b>CUFF</b>	3.8mil	0.10mm
<b>COLOR</b>	<b>OUTER</b>	Green	
	<b>INNER</b>	White	
<b>SURFACE</b>	<b>OUTER</b>	Fully Textured	
	<b>INNER</b>	EnerGel®	
<b>LENGTH</b>	9.5"	242mm	
<b>WEIGHT</b>	6.5g		
<b>FIT TYPE</b>	Ambidextrous		
<b>CUFF TYPE</b>	Beaded		
<b>WATERTIGHT AQL</b>	1.5		
<b>ORIGIN COUNTRY</b>	China		

Specifications based on size Large glove

### PHYSICAL PROPERTIES

	PRE-AGING	POST-AGING
<b>TENSILE STRENGTH:</b>	18 MPa	18 MPa
<b>ELONGATION:</b>	550%	500%

### INTEGRATED TECHNOLOGIES

**ENERGEL** Hand Conditioning Technology: allows for thorough penetration of Aloe Vera into the skin, reduces water loss to retain moisture and has been clinically proven to prevent many skin ailments, like dermatitis.

**ECOTEK** Biodegradable Technology: 92.6% biodegradable in 2.5 years. ASTM D5526-12 test results do not predict future biodegradation.\*


**BREACH ALERT** Visual Detection Technology: provides durable 2-ply construction and contrasting inner color



## STANDARDS & CERTIFICATIONS

EN ISO 21420:2020  
EN 455-2000-2015  
ASTM D6319-19  
ASTM D6978-05 (2019)  
ASTM F1671-13  
ASTM F739-12  
Reach EU 1907/2006

EU 2016/425  
CAT III Complex Design  
UL NFPA 1999-2018  
FDA 21 CFR 177.2600



Please visit [swsafety.com/symbols](http://swsafety.com/symbols) for information on standards used on this document.

## ORDERING

ITEM NO.	SIZE	PALM WIDTH	PACKAGING
N189471	XS 5½ – 6	2.7" 70mm	50 gloves per box 10 boxes per case
N189472	S 6½ – 7	3.1" 79mm	50 gloves per box 10 boxes per case
N189473	M 7½ – 8	3.5" 89mm	50 gloves per box 10 boxes per case
N189474	L 8½ – 9	4.1" 104mm	50 gloves per box 10 boxes per case
N189475	XL 9½ – 10	4.5" 114mm	50 gloves per box 10 boxes per case
N189476	2XL 10½ – 11	4.9" 124mm	50 gloves per box 10 boxes per case

## APPLICATIONS

### INDUSTRIAL

Agriculture  
Hydroponics  
Assembly

### MEDICAL

Chemical Handling  
First Responder EMS  
Clinical  
Laboratory  
Liquid Handling  
Pharma Production

Keep out of sunlight. Store in a cool, dry place.  
Keep away from sources of ozone or ignition.



R\_N18947X1121



SW®  
33278 Central Avenue, Unit 102, Union City, CA 94587, USA  
Tel: +1.510.429.8692 | Fax: +1.510.487.5347

Trademarks and registered trademarks are the property of SW and its affiliates.  
©2022 SW. All rights reserved.



\*Under test method ASTM D5526-12, a standard test method for determining anaerobic biodegradation of plastics in accelerated landfill conditions. Current biodegradation results do not predict future results.